

Galaxy International FZC



Paint and Printing Ink Raw Material



Zinc by-product and HG ingots

Zinc

Zinc Specification *

Zinc Powder: Pipe Galvanizing

H2O	0.14%
METALLIC ZN	93.5%
CL	0.13%
FE	0.17%
PB	0.59%
CU	0.003%
CD	0.0001%
AL	LESS THAN 0.003%
SN	LESS THAN 0.003%



Zinc Dross: Galvanizing

Zinc	- 92 to 94% Min
Pb	- 1 to 2% Max
Fe	- 4% Max
Cd	- 0.001% Max
Al	- 0.1% Max



Zinc Ash – Galvanizing

Zinc	- 70 to 75% Min
Fe	- 1% Max
Lead	- 1 to 2% Max



Zinc Ingots (HG)

Zn	- 99.95%
Pb	- 0.03% (Max)
Cd	- 0.01% (Max)
Fe	- 0.02% (Max)
Al	- 0.01% (Max)
Sn	- 0.001% (Max)
Cu	- 0.002% (Max)



Contact for purchase and sell:

PO BOX 8713

Sharjah – UAE

Tel: 00 971 6 557 08 20

Email: galaxy@galaxyfzc.com

* Specification may vary depending on the material coming from various galvanizing units